

_____ COARSE AGGREGATE

NOTE TO SPECIFIERS: For concrete work in the Kansas-Nebraska area, special changes and additions to this paragraph will be necessary. When preparing specifications for concrete work in this area, contact code D-1511, Engineering and Research Center, for specific requirements.

- a. General. - For the purposes of these specifications, the term "coarse aggregate" designates clean, well-graded aggregate of particle sizes within the range of $\frac{3}{16}$ of an inch to ¹(1-1/2 inches) or any size or range of sizes within such limits. Coarse aggregate for concrete shall consist of natural gravel or crushed rock or a mixture of natural gravel and crushed rock.
²(Jaw crushers shall not be used except as a primary crusher. If crushed coarse aggregate is used with natural coarse aggregate, the crushed aggregate shall be blended uniformly with the natura