

RECLAMATION

Managing Water in the West

Review of Corrosion Inhibiting Mechanisms in Coatings

Research and Development Office
Science and Technology Program
(Final Report) ST-2017-1703



U.S. Department of the Interior
Bureau of Reclamation
Research and Development Office

September 2017

The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.

PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.

1. REPORT DATE (DD-MM-YYYY) September 2017		2. REPORT TYPE Research		3. DATES COVERED (From - To)	
4. TITLE AND SUBTITLE Review of Corrosion Inhibiting Mechanisms in Coatings				5a. CONTRACT NUMBER 17XR0680A1-RY15412017IS11703	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER 1541 (S&T)	
6. AUTHOR(S) Stephanie Prochaska, sprochaska@usbr.gov , 303-445-2323 Dave Tordonato, dtordonato@usbr.gov , 303-445-2394				5d. PROJECT NUMBER ST-2017-1703	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER 86-68540	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Bureau of Reclamation Denver, CO				8. PERFORMING ORGANIZATION REPORT NUMBER 8540-2017-047	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Research and Development Office U.S. Department of the Interior, Bureau of Reclamation PO Box 25007, Denver CO 80225-0007				10. SPONSOR/MONITOR'S ACRONYM(S) R&D: Research and Development Office BOR/USBR: Bureau of Reclamation DOI: U.S. Department of the Interior	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S) ST-2017-1703	
12. DISTRIBUTION/AVAILABILITY STATEMENT Final report can be downloaded from the Bureau of Reclamation's Web site: https://www.usbr.gov/research/					
13. SUPPLEMENTARY NOTE					
14. ABSTRACT Modern coatings used by the Bureau of Reclamation have service lives of 20–25 years, whereas legacy coatings that contained red lead and chromate pigments had service lives of over 50 years. The mechanisms of corrosion protection of lead- and chromate-based coatings were researched, and literature was analyzed to identify nontoxic substitutes for these pigments. All inorganic pigments analyzed exhibited corrosion prevention mechanisms similar to that of red lead, in which metal soaps were formed with certain binders, and, in a secondary mechanism, the surface of the substrate was passivated. Conducting polymers, specifically pigments of polyaniline, were also found to be potential substitutes. The greatest challenge moving forward is to be able to quickly and objectively test commercially available coatings containing nontoxic pigments to determine if they perform as well as coatings that contained red lead or chromate.					
15. SUBJECT TERMS anticorrosion coatings, corrosion inhibitors, lead paint, inhibiting pigments					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT U	18. NUMBER OF PAGES 41	19a. NAME OF RESPONSIBLE PERSON Stephanie Prochaska
a. REPORT U	b. ABSTRACT U	a. THIS PAGE U			19b. TELEPHONE NUMBER (Include area code) 303-445-2323

Review of Corrosion Inhibiting Mechanisms in Coatings

**Research and Development Office
Science and Technology Program
(Final Report) ST-2017-1703**



**U.S. Department of the Interior
Bureau of Reclamation
Research and Development Office**

September 2017

MISSION STATEMENTS

Protecting America's Great Outdoors and Powering Our Future

The Department of the Interior protects and manages the Nation's natural resources and cultural heritage; provides scientific and other information about those resources; and honors its trust responsibilities or special commitments to American Indians, Alaska Natives, and affiliated island communities.

Disclaimer:

This document has been reviewed under the Research and Development Office discretionary peer review process https://www.usbr.gov/research/peer_review.pdf consistent with Bureau of Reclamation (Reclamation) Peer Review Policy CMP P14. It does not represent and should not be construed to represent Reclamation's determination, concurrence, or policy.

BUREAU OF RECLAMATION
Research and Development Office
Science and Technology Program

**Materials and Corrosion Laboratory, Technical Service
Center, 86-68540**

Final Report ST-2017-1703

**Review of Corrosion Inhibiting
Mechanisms in Coatings**

STEPHANIE PROCHASKA Digitally signed by STEPHANIE PROCHASKA
Date: 2017.09.19 11:05:43 -06'00'

Prepared by: Stephanie Prochaska, M.S.
Materials Engineer, Materials and Corrosion Laboratory,
86-68540

Date

BOBBI JO MERTEN Digitally signed by BOBBI JO MERTEN
Date: 2017.09.19 09:54:30 -06'00'

Checked by: Bobbi Jo Merten, Ph.D.
Chemist, Materials and Corrosion Laboratory, 86-68540

Date

ALLEN SKAJA Digitally signed by ALLEN SKAJA
Date: 2017.09.19 16:43:57 -06'00'

Technical Approval: Allen Skaja, Ph.D.
Chemist, Materials and Corrosion Laboratory, 86-68540

Date

DAVID TORDONATO Digitally signed by DAVID TORDONATO
Date: 2017.09.19 09:19:12 -06'00'

Peer Review: David Tordonato, P.E., Ph.D.
Materials Engineer, Materials and Corrosion Laboratory,
86-68540

Date

ACKNOWLEDGMENTS

This research was funded through Science and Technology Program project ID 1703. David Tordonato, Allen Skaja, and Bobbi Jo Merten provided invaluable experience, guidance, and suggestions to ensure the completion of this report. Their contributions and continuous support are greatly appreciated.

ACRONYMS AND ABBREVIATIONS

A _e	anticorrosion efficiency
c/PANI	polyaniline-coated graphite
PANI	polyaniline
PmAS	poly(m-anisidine)
PoAP	poly(o-aminophenol)
PoAT	poly(m-anisidine)
Reclamation	Bureau of Reclamation
UV	ultraviolet

Symbols

>	greater than
<	less than

CONTENTS

	Page
Executive Summary	ES-1
Introduction.....	1
Coatings Basics	1
Corrosion Basics	2
Cost of Corrosion	3
Inhibitive Coatings Corrosion Protection Mechanism.....	4
Red Lead Pigments	5
Chromate Pigments	5
History of Inhibitive Pigment Use on Reclamation's Structures.....	6
Red Lead Primer	6
Chromates	7
Modern Inhibitive Pigments	8
Modern Pigments	9
Inorganic Pigments	9
Organic Pigments.....	12
Metallic Pigments	15
Conclusion	15
Recommendations for Future Work.....	16
References.....	19

Tables

Table	Page
1 Original red lead coating date of structures at various Reclamation facilities.....	7
2 Anticorrosion efficiency of polyaniline-coated graphite (C/PANI), reproduced from reference [2]	13
3 Corrosion rate data for a series of poly(aromatic amines) [3]	14

Figures

Figure		Page
1	Corrosion mechanism for steel.	3
2	Lead-coated penstock exteriors at Flatiron Powerplant in 2007. The exteriors were recoated with a zinc-rich primer and polyurethane topcoat in 2010.....	6
3	Red lead service life on various structures at Reclamation facilities.....	8
4	Phosphates contain a phosphorous and an oxygen functional group, designated as “R”.....	9
5	Zinc molybdate structure.	11
6	Zinc silicate structure.	11

Attachments

Attachment

- A Supporting Information

EXECUTIVE SUMMARY

Legacy coatings used by the Bureau of Reclamation (Reclamation) to protect the metalwork associated with water infrastructure often had service lives of 50 years or more. These coatings, however, contain toxic pigments such as red lead and chromate and are no longer specified for use. The currently specified coating systems, such as epoxies, have service lives of only 20–25 years, which results in extra costs incurred by Reclamation to recoat structures more frequently.

The long service lives of legacy coatings can be attributed to certain pigments within coatings that are considered corrosion inhibitors. Usually, a coating works to prevent corrosion by three general mechanisms: a physical barrier to prevent corrosive species from reaching the steel substrate, a sacrificial coating to corrode instead of the steel substrate, and a corrosion inhibitor that undergoes chemical reactions with the corrosive species to stop or impede corrosion. Since lead- and chromate-based coatings are no longer used by Reclamation, barrier and sacrificial coatings are the only types that are currently specified.

Red lead and chromate-based paints work well because they are inhibiting pigments. In the case of red lead-based coatings, the lead tetroxide pigments react with a component of the coating's binder to form a metal soap. These soaps degrade into a water-soluble lead salt, which can migrate to defects and inhibit corrosion by reacting with specific ions to form a stable, insoluble compound. As a secondary mechanism, lead tetroxide also passivates the metal, rendering the surface of the substrate unreactive by forming a thin, inert layer of oxides.

This literature review aimed to identify nontoxic inhibitive pigments that prevent corrosion using the same or similar mechanisms as lead and chromate pigments. Three broad categories of pigments were researched: inorganic, organic, and metallic. Inorganic pigments showed the most promise for becoming a replacement for lead. Of the four broad types of inorganic pigments researched (phosphates, molybdates, silicates, and ferrites), findings indicated that all can form metallic soaps in certain types of binder systems, specifically oleoresinous systems. The presence of zinc also seemed to be an important factor for soap formation. Strontium and calcium were also common additions.

Much of the research surrounding organic inhibiting pigments focuses on conducting polymers. Polymers that conduct electricity and act as a strong oxidant to steel result in shifting the potential to the noble direction and induce passivation. Polyaniline is the most commonly studied conducting polymer, and it has shown good promise as a corrosion inhibiting pigment [1]. In one study, polyaniline coated with graphite significantly outperformed other tested pigments, including a commercially available pigment specifically branded as “anticorrosive” [2].

Polyaniline was also tested against other organic polymers, including poly(m-anisidine) (PmAS) [3]. In that study, it was found that the chelating efficiency of the polymer greatly impacted its corrosion resistance. PmAS had a greater chelating efficiency than the other polymers and more reactive functional groups, giving it the best corrosion-resistant properties.

Metallic pigments, especially zinc pigments, inhibit corrosion by acting as sacrificial pigments and corroding preferentially to steel. Aluminum pigments have also been found to be inhibitors, particularly when coated with silica, a semiconductor. In another study, aluminum flakes were shown to form tightly interlocking structures on steel substrates and impede the movement of corrosion species to the steel.

A significant amount of work is being done to identify inhibitive pigments that can replace lead and chromate. However, it is exceedingly difficult to compare each individual research study, thus each pigment's performance, to one another. Further complicating matters, some pigments require a lag time when exposed to an aqueous environment before their corrosion prevention mechanisms are fully enabled. This issue would make it difficult to equally compare the coatings' performances in accelerated laboratory tests.

The first step to continue this research is to analyze current, commercially available coating systems that contain inhibitive pigments identified in this review and determine their expected failure mechanism. Knowing how the coating will fail will aid in predicting when it will fail—potentially saving valuable testing time. Next, accelerated laboratory testing aimed at emulating atmospheric service should be performed on the coatings to quickly determine their performance against one another. To account for the lag time that some pigments exhibit, it is suggested that those coatings undergo preconditioning in a humid environment (depending on typical lag times) prior to accelerated testing.

INTRODUCTION

Protective coatings prevent corrosion by one or a combination of three mechanisms: barrier protection, sacrificial (galvanic) protection, and corrosion inhibitive pigments. The first two mechanisms are not complex. Barrier coatings contain binders and pigments designed to impede the migration of an electrolyte to a substrate. Sacrificial pigments corrode preferentially to steel to prevent corrosion. Corrosion inhibitors generally function by disrupting the corrosion reaction typically through a competing reaction, but the exact mechanism or reaction depends on the specific pigment type.

Lead-based paints are a good example of a coating that utilizes inhibitive pigments to prevent corrosion. “Red lead” (lead tetroxide, Pb_3O_4) was used extensively within the Bureau of Reclamation (Reclamation) and industry in atmospheric service environments to provide corrosion protection to steel lasting upwards of 50 years. However, the exact mechanism for the success of lead paint is still not fully understood. Lead paints have been largely phased out due to environmental, health, and safety hazards. However, existing lead coatings continue to provide excellent corrosion protection on many Reclamation structures. Replacing old legacy coating systems such as lead-based paint with safe and modern equivalents is an important but challenging proposition for Reclamation. Many of the coatings specified today rely solely on barrier protection and provide a fraction of the service life, at 20–25 years, versus legacy coatings (50+ years).

This literature review aims to determine what other corrosion inhibitive pigments are available for use on steel infrastructure – specifically, how Reclamation can achieve similar anticorrosion performance (as lead-based paints) using environmentally compliant inhibitors or materials in coatings.

COATINGS BASICS

Most polymeric coatings contain multiple components: resin (binder), solvent, additives, and pigments. Corrosion inhibitors are part of the binder, additives, or pigments.

The binder is the backbone of the coating, and it provides most of the coating’s features and functions. The type of binder used (acrylic, epoxy, polyurethane, etc.) usually lends its name to the generic coating name. Binder resins protect the substrate by wetting out the surface and adhering to it as a cured or dried film. Therefore, the resins transform from a liquid to a solid during film formation. Binders provide barrier protection for the underlying metal substrate, protecting the substrate from cathodic reactants such as oxygen, water, and corrosive anions [4]. However, binders are inherently permeable, and corrosive agents will reach the substrate at varying rates.

Solvents are added to a binder or resin to transform them into a liquid state or to reduce viscosity during application. The two most important properties of a solvent in a coating system are the solvency power, or the ability of the solvent to dissolve the resin or binder, and the volatility, or how quickly the solvent will evaporate from the coating after it has been applied. Once the coating is applied and cured, the solvent has no remaining role in the coating system. Some coating systems are formulated without any solvent at all.

Additives are important in providing coating systems with their unique properties and are added to perform a specific function. Additive functions can ensure coating stability, aid application and increase pot life, provide added ultraviolet (UV) resistance, increase shelf life, and influence curing times.

Pigments are discrete particulate solids that do not dissolve in the coating. Pigments are used for corrosion protection, to impart color, to increase water resistance, and to modify the coating's mechanical or electrical properties.

CORROSION BASICS

Corrosion is an electrochemical reaction that deteriorates a metal or an alloy [5]. Reclamation's structures are particularly susceptible to this deterioration based on their proximity to bodies of water and atmospheric exposure. Structures like gates, valves, penstocks, piping, and other exposed features are among some of the most prone to corrosion from condensation, spray, rain, and other environmental conditions.

Corrosion of steel requires four elements to complete the electrochemical cell: an anode (the metal that readily gives up electrons), a cathode (the metal that readily accepts electrons), an electrolyte (the liquid that helps the electrons move), and a metallic pathway for electron movement. The interaction of these elements is also known as a corrosion cell. Corrosion inhibitors interrupt the corrosion cell by removing one of these elements.

In general corrosion of steel, the steel acts as the anode, with adjacent areas acting as cathodes. In order to complete the corrosion cell, the steel is also a metallic pathway, and water or soil can be the electrolyte [6, 7].

Elemental iron is naturally unstable and releases electrons at the anode in the presence of oxygen to become a more stable ferrous iron, Fe^{2+} [8]. Those electrons move to the nearby cathodic sites on the surface, forming hydroxyl ions (OH^-) as they combine with oxygen and water. The Fe^{2+} from the anode reacts with the OH^- at the cathode to produce ferrous hydroxide and ultimately red rust.

Figure 1, below, depicts the corrosion mechanism for steel.




Figure 1: Corrosion mechanism for steel.

In general, the rate of corrosion is determined by the electrolyte and the difference in nobility between the metals or the area of steel, with the galvanic series determining which material is most noble. Typically, the more noble material, the cathode, is more resistant to corrosion than the less noble material, or the anode. Over long periods of time, the loss of metal from anodic sites is fairly uniform over the surface. This type of corrosion is known as general corrosion and usually does not result in catastrophic failure, although preventative measures should still be taken to prevent it. Pitting corrosion and crevice corrosion are considered localized corrosion and are more commonly associated with catastrophic failures of the structures. In both cases, there can be severe or complete loss of material from the anodic area if not detected.

Cost of Corrosion

NACE International estimated that the global cost of corrosion is \$2.5 trillion, approximately 3.4 percent of the global gross domestic product [9]. In the United States alone, corrosion is estimated to cost over \$276 billion, with \$22.6 billion in costs directly associated with the corrosion of infrastructure [10]. If optimum corrosion management practices were employed, NACE estimates that 25–30 percent of this cost could be saved.

INHIBITIVE COATINGS CORROSION PROTECTION MECHANISM

Inhibitive coatings are typically included in the primer, or the first coat, of a coating system where they are in contact with the substrate to be effective. In general, inhibitive coatings reduce the rate of an electrochemical reaction that causes corrosion through the use of pigments.

Inhibiting pigments' various physical and chemical factors limit the rate of an electrochemical reaction by stunting or polarizing it [11]. Polarization can be anodic or cathodic and is the shift of electrode potential resulting from a net current. In cathodic polarization, electrons are sent to the substrate. Slow reaction rates cause a buildup of electrons, and the surface potential becomes negative. In anodic polarization, electrons are emitted from the metal. This deficiency causes a positive potential on the surface.

Coatings utilizing inhibitive pigments release soluble species from the pigment into the electrolyte once it has saturated the coating [12]. These species inhibit corrosion in a process called passivation by facilitating the growth of protective surface layers.

When metals lose chemical reactivity, it is called passivation. The metals are rendered inert and act more noble due to the formation of thin, tightly adherent oxide layers. There are two mechanisms of passivation: imposed passivation, which occurs by anodic polarization of the metal, and spontaneous passivation, which occurs in the presence of an oxidant [13]. Near-insoluble compounds are formed when a metal becomes anodic in a solution that only contains anions [11].

Sinko describes all active corrosion inhibitor pigments as inorganic salts with the general formula $A_m^{n+}B_n^{m-}$ [14]. Since corrosion is an aqueous process, corrosion inhibitor activity of pigments can be specifically characterized by their solubility in water. In general, the solubility of these pigments ranges from sparingly to slightly soluble. Thin, inert oxide layers form on the substrate when the solubility of pigments at saturation and normal temperature (expressed in molar concentration) is greater than the critical concentration of the anion, B^{m-} . Therefore, the anion inherently influences the rate of corrosion. The salt's cation has little effect on the pigment's inhibitive properties (with one exception being Zn^{2+}).

Inhibitive pigments can also protect macroscopic defects by leaching out from adjacent areas into the defect [15]. This self-healing mechanism, also known as active corrosion protection, is most commonly associated with coatings containing chromate pigments and is discussed in more detail under the "Chromate Pigments" section.

Red Lead Pigments

The two oxides of lead are litharge (PbO) and red lead (Pb_3O_4) [16]. Litharge, a yellow substance, is formed when elemental lead reacts with oxygen as it is melted. Upon further heating, the unstable litharge becomes red lead when it is oxidized. One of the first recorded pigment inhibitors, red lead has been used widely in primers for structural steel [17].

Sparingly soluble (solubility of < 0.001 percent) lead pigments are not actually direct inhibitors, but they can react with certain resin systems, linseed oils, or other oils to form metal soaps that are active inhibitors and appear to be the mechanism by which lead pigments inhibit corrosion on both new and rusted steel [18, 19, 20]. These soaps degrade into water-soluble lead salts, which can migrate to defects and inhibit corrosion by reacting with certain ions to form a stable, insoluble compound. Soluble lead compounds and organic acids are then released in the presence of water and oxygen as fatty acids degrade [21]. Examples of lead salts are azelaic acid ($\text{C}_9\text{H}_{16}\text{O}_4\text{Pb}$), suberic acid ($\text{C}_8\text{H}_{14}\text{O}_4\text{Pb}$), and pelargonic acid ($\text{C}_9\text{H}_{18}\text{O}_2\text{Pb}$), which have been proven to be corrosion inhibitors [22, 23].

These salts lower the pH of a solution by contributing hydrogen ions as it hydrolyzes water and produces iron(III) oxide-hydroxides. The liberated hydrogen promotes passivation by strengthening the metal's oxide film until it becomes impermeable, impeding corrosion [24]. According to Mayne and Ramshaw, the inhibitive efficiency of lead salts increases with the length of the carbon chain to a maximum of 9 carbon atoms [25]. This effect can be attributed to a compound's enhanced surface activity. In addition, the polar functional groups containing oxygen atoms are adsorbed onto the steel substrate and act as barriers blocking corrosion sites [26].

Chromate Pigments

Although chromates have not been used as extensively as lead throughout Reclamation's history as corrosion inhibitive pigments, they are among the most efficient passivators. Generally, hexavalent (Cr^{6+}) chromium (a strong oxidizer) and trivalent (Cr^{3+}) chromium ions provide high corrosion resistance to chromate coatings [27]. When under corrosive attack, the hexavalent chromium undergoes active corrosion protection and reduces to form trivalent chromium. The insoluble trivalent chromium can then end the attack.

Coating manufacturers have been able to tailor chromate's ability to dissolve and release ions due to the wide range of solubilities of different chromate pigments [22]. If the solubility is too high, and the pigment is under long-term moisture conditions, blisters may form. Chromate pigments are therefore not suitable for use in immersion conditions or other conditions with long periods of exposure to moisture.

In general, use of chromates as inhibitive pigments in coatings is declining due to health and environmental concerns, and regulations prevent Reclamation from using them.

HISTORY OF INHIBITIVE PIGMENT USE ON RECLAMATION'S STRUCTURES

Red Lead Primer

Alkyd primers and drying oils containing “red lead” had been used extensively by Reclamation to protect its structures, specifically formulations TT-P-86 type I linseed oil, II Linseed oil/alkyd, III alkyd, and IV phenolic resin tung oil. Types I, II, and III were specifically used for atmospheric exposure only; type IV could be used in immersion service. Application on the exterior of penstocks and on bulkhead gates was most common. Figure 2, below, shows the lead-coated penstock exteriors at Flatiron Powerplant in 2007.



Figure 2: Lead-coated penstock exteriors at Flatiron Powerplant in 2007. The exteriors were recoated with a zinc-rich primer and polyurethane topcoat in 2010.

A Reclamation analysis of some of these structures revealed that the average service life of red lead primer was 64 years. This value was calculated by only considering the service lives of the red lead primer on the structures that have since been repainted.

Table 1, below, depicts the original red lead coating date of structures at various Reclamation facilities.

Table 1: Original red lead coating date of structures at various Reclamation facilities

Facility	Structure	Original coat date
Colorado River Basin Salinity Control Project*	Delivery piping and valve seat	1985
Crystal Dam*	Exterior penstock	1977
Flatiron Dam	Exterior penstock	1954
Grand Coulee Dam*	Exterior discharge tube, interior spiral case	1950
Havasu Pumping Plant*	Structural steel, tanks, bulkhead gate	1978
Parker Dam	Bulkhead gate	1938
Pole Hill Powerplant	Bulkhead gate	1951
Southern Nevada Water Project*	Unspecified	1970

* Denotes a structure with original red lead coating.

Figure 3 shows the service life of red lead primer on various structures at Reclamation facilities. The data represent all “as reported” information obtained from historical coatings submittals and other documents.

Notably, there are some facilities with structures that still have the original red lead coating (designated by *). These original coatings are all currently over 30 years old. All of the repainted structures had red lead primer service lives of at least > 50 years, with the red lead primer on the bulkhead gates at Parker Dam in California having the longest service life of 77 years.

While it was not possible to obtain accurate coatings data from all structures at Reclamation’s facilities, this survey shows the efficacy and longevity of red lead primer as an inhibitive pigment coating.




Figure 3: Red lead service life on various structures at Reclamation facilities.

Chromates

Chromate pigments, typically in the form of zinc chromates under Federal specification TT-P-636, were also found to have been used at some of Reclamation's facilities. Structures coated with zinc chromate primer included the exterior of penstocks at Coolidge Dam in Arizona, exterior housings at the Gallegos Pumping Plant in New Mexico, and access bridges at Jordanelle Dam in Utah, among others.

Reclamation did not use zinc chromate primers until the mid-1980s, when they were required to remove lead-based paints from their specifications. The analysis showed use of zinc chromate primers as late as 1995. None of the structures coated with the zinc chromate primer have been repaired or recoated as of 2017. Existing chromate primers on Reclamation's structures have already met or exceeded the 20–25 year service lives expected for modern coating systems currently specified [28].

Modern Inhibitive Pigments

Lead and chromate pigments have been found to be highly toxic. Among unfavorable health effects, extensive exposure to lead-based paints has been shown to cause motor neuron disease [29], and chromates are

carcinogenic [30]. The continued use of these elements has become undesirable, and coatings containing them are almost completely nonexistent.

Historically, Reclamation has used coating systems containing lead and chromate pigments. Reclamation discontinued use of paints and coatings containing lead and chromate in the 1980s and 90s but without an equal substitute replacement.

There is a need for Reclamation to use coatings that provide much longer service lives than the current offerings. Understanding the corrosion protection mechanisms of red lead and chromate pigments may provide information in finding modern inhibitive pigments that may provide better corrosion protection.

Modern Pigments

For the purpose of this review, modern pigments will be regarded as those that are nontoxic (lead and chromate free). The three general classes of modern inhibitive pigments are inorganic pigments, organic pigments, and metallic pigments.

Inorganic Pigments

Inorganic pigments are made from compounds that are not based on carbon and are usually metallic salts precipitated from solutions. This review will discuss the corrosion prevention mechanisms of four general groups of inorganic pigments: phosphates, molybdates, silicates, and ferrites.

Phosphates

Phosphates refer to a wide variety of pigments that contain a phosphorous and an oxygen functional group as seen on figure 4, below [22].




Figure 4: Phosphates contain a phosphorous and an oxygen functional group, designated as “R”.

One of the most common and effective phosphate-based corrosion inhibitors are zinc phosphates. Zinc phosphates are extremely versatile due to their low solubility and can be used with many different types of binders and resins in a variety of coating systems [31].

There are multiple mechanisms through which zinc phosphates provide corrosion protection. Slight hydrolysis of zinc phosphate occurs as water enters the coating. This hydrolysis results in the formation of secondary phosphate ions that prevent anodic corrosion by forming a protective passive layer on the substrate [32]. Another mechanism requires the presence of soluble zinc phosphate pigments. A protective film of $\gamma\text{-Fe}_2\text{O}_3$ that prevents the diffusion of iron can be created on the anode when dissolved oxygen is adsorbed onto the metal [33]. Phosphate ions complete or maintain the film by filling gaps with anion precipitates of Fe(III) ions. In another mechanism, when the zinc phosphate becomes hydrated and dissociated, it can create complexes with components of some specific binders. Much like the mechanism that gives red lead good anticorrosion properties, metal soaps (and subsequently, salts) are formed through the reaction [34]. Finally, the substrate can become polarized due to the adherence of insoluble salts that prevent dissolved oxygen from nearing the surface. These salts also polarize the substrate's cathodic areas [35].

Due to their very low solubility, zinc phosphates commonly perform poorly in accelerated testing despite performing well in the field [36]. This can be explained by the theory that the protective phosphate complex forms slowly on a substrate, creating an initial lag time that cannot be sped up in accelerated testing. Corrosion initiation in the field typically takes longer than the formation of the protective complex on the substrate; however, in accelerated testing, time to corrosion occurs much more quickly, causing unfavorable results.

Zinc phosphates are not the only phosphate-based compound that can prevent corrosion. Hydrated dihydrogen aluminum triphosphate is an acid that, when dissolved, can dissociate into triphosphate ions [37]. The triphosphate ions can then passivate the substrate by chelating with iron ions. An insoluble layer of ferric triphosphate is formed when the anion $(\text{P}_3\text{O}_{10})^{5-}$ reacts with anodic iron. Unlike other phosphate compounds, the corrosion protection can be entirely attributed to the phosphate.

Molybdates

Molybdates refer to pigments that involve a molybdenum- and oxygen-containing anion with molybdenum in its highest oxidation state [38]. Molybdates passivate the substrate, forming an insoluble, protective layer of ferric molybdates on the surface of steel, inhibiting the anodic corrosion reaction. In addition, when they contain zinc, molybdate pigments can also form inhibitive zinc soaps in certain binders. Figure 5, below, shows the formula for zinc molybdate.




Figure 5: Zinc molybdate structure.

In general, tests of these pigments as corrosion inhibitors in paint formulations have had varied results [22]. One main disadvantage is that molybdates experience premature binder aging, which can cause coating embrittlement [39]. Another drawback of molybdate pigments is that they are relatively expensive compared to other types of pigments. To lower costs and improve adhesion, zinc phosphate versions of the molybdate pigments have been considered [40]. Molybdates are thought to be nontoxic; however, according to the American Conference of Governmental Industrial Hygienists, they can release toxic fumes when subjected to cutting or welding [41]. In addition, molybdates have been found to be toxic to some freshwater and marine organisms [42].

Silicates

Silicates refer to pigments containing silicon and oxygen [22]. The most common, nontoxic metals used in silicate pigments are calcium, strontium, and zinc. Figure 6, below, shows the formula for zinc silicate.




Figure 6: Zinc silicate structure.

Much like the mechanism of red lead, silicates can react with oleoresinous binders to form metal soaps of barium, calcium, strontium, and zinc. Mayne observed that these metal soaps, specifically the metal soaps formed from calcium phosphosilicate and borosilicate, degrade and form products containing soluble, inhibitive anions [43]. As a secondary inhibition mechanism, it was also observed that the alkalinity near the substrate had increased.

Ferrites

Ferrites refer to pigments composed of Fe_2O_3 and another metal, typically magnesium, calcium, strontium, barium, zinc, or manganese.

Similarly to red lead, ferrite pigments also protect steel by reacting with fatty acids in the binder to form metal soaps [44]. Further corrosion protection is achieved by the formation of an alkaline environment at the interface between the coating and the substrate. This alkaline environment promotes the passivation of the metal.

Ferrite pigments were also tested in an epoxy binder, which does not usually produce soap with metal ions [45]. When analyzed using electrochemical impedance spectroscopy, all ferrite pigmented epoxy coatings performed better after immersion in a 3-percent sodium chloride (NaCl) aqueous solution than the red lead pigments in the same binder. However, there was a noted lag time between the initial immersion and passivation due to the time it took for the water to permeate the coating and reach the interface between the coating and the substrate.

Organic Pigments

Organic pigments are based on carbon chains and carbon rings. They can also contain inorganic elements to help stabilize the properties of the organic component. Most organic corrosion inhibiting pigments can form tightly packed complexes with the substrate, thus blocking active sites as an additional mechanism of protection [4].

Conducting polymers (organic polymers that conduct electricity) have been an intriguing area of research since their discovery in the 1970s [1]. Conducting polymers have more positive corrosion potentials than those of metals, enabling them to preferentially undergo reactions with corrosive species [46]. In addition, they are theorized to release dopant ions in the presence of electrolytes and are then re-oxidized by oxygen [47]. These polymers are nontoxic and are highly permeable to liquids and gases due to their porous structure [2]. Their impact on the field of science was recognized in 2000 by the awarding of the Nobel Prize for Chemistry to the researchers who discovered them [48].

The most studied conducting polymer is polyaniline. Polyaniline has been shown to provide multiple mechanisms of corrosion protection, including barrier effect and internal sacrificial electrode formation, in which the polymer reduces cathodic reactions by transferring them from a metal-electrolyte interface to an electrolyte-polymer interface [49]. Wessling et al. have further suggest that passivating oxide layers are formed when polyaniline is galvanically coupled with steel [50]. This work suggests that polyaniline functions similarly to chromate with its self-healing properties: the steel substrate is automatically passivated if a scratch or breach in the coating develops.

Kalendova, in 2008, experimented with coating graphite pigments with polyaniline [2]. Graphite has good conductivity, thus enhancing the properties of

the polyaniline by ensuring the efficient transport of electrons involved in the reduction-oxidation processes. Graphite's flat, lamellar structure also promoted barrier formation while ensuring favorable contact with the substrate [2]. Graphite's structure also gives the pigment excellent mechanical properties such as good adhesion, impact resistance, and ductility.

Table 2, below, shows the polyaniline-coated graphite (C/PANI) pigment's anticorrosion efficiency, A_e , after 500 hours in a condenser chamber. The graphite/polyaniline pigment outperformed all other tested pigments, including a patented "anticorrosion pigment" composed of silicate zinc-strontium-calcium hydrated phosphate. In table 2, "PANI" is polyaniline.

Table 2: Anticorrosion efficiency of polyaniline-coated graphite (C/PANI), reproduced from reference [2]

Pigment	Surface blistering	Corrosion in a cut (millimeters)	Surface corrosion (percent)	Anticorrosion efficiency (A_e)
C	–	0.5 – 1	3	83
PANI	8MD	0 – 0.5	3	65
C/PANI	–	0 – 0.5	0.03	97
α -Fe ₂ O ₃	4M	1 – 2	50	38
α -Fe ₂ O ₃ /PANI	6M	1 – 2	16	53
"Anticorrosion pigment"	8D	1 – 2	3	51
Binder without pigment	2MD	2 – 3	33	33

The data in table 2 were obtained using the following standards: ASTM D714-87: "Evaluating Degree of Blistering of Paints" [51], ASTM D1654-92: "Evaluation of Painted or Coated Specimens Subjected to Corrosive Environments" [52], and ASTM D610-85: "Evaluating Degree of Rusting on Painted Steel Surfaces" [53].

Other types of organic polymer pigments have also been studied to determine their corrosion inhibitive properties. In a 1998 study by Abd El-Ghaffar et al., a series of poly(aromatic amines) were prepared and incorporated into various paint formulations to replace the typical, toxic inhibitive pigments [3]. Poly(o-aminophenol), or PoAP; poly(o-aminothiophenol), or PoAT; poly(m-anisidine), or PmASl; and polyaniline were prepared by chemical oxidation of their monomers using ammonium persulfate. Figure 7 depicts the monomers of PoAP, PoAT, PmAS, and polyaniline. The study found that all of the polymer pigments inhibited corrosion more than the control, which did not contain a coating with an inhibitive polymer pigment. Table 3 shows the corrosion rate data for each polymer at 1.0 percent concentration.




Figure 7: Monomers of polyaniline (top left), PoAT (bottom left), PoAP (top right), and PoAS (bottom right).

Table 3: Corrosion rate data for a series of poly(aromatic amines) [3]

Polymer	Average weight loss (grams)	Corrosion rate x 10 ² (mg/cm ² per day)
Blank	0.0160	57.15
Polyaniline	0.0083	29.64
PoAP	0.0082	28.30
PoAT	0.0077	27.50
PoAS	0.0076	26.14

The authors concluded that the mechanism of corrosion inhibition was related to the chelating efficiency of each material (i.e., the ligand's ability to bond to a central metal atom at two or more points). This chelation effect, thus the corrosion inhibition, is a result of the delocalized electrons on the nitrogen atoms forming a thin layer of metal-polymer complex between the steel substrate and the nitrogen. The other groups on the ring (e.g., OH, SH, and OCH₃) contribute their own free electrons, and the corrosion rate is attributed to the order of chelation efficiency of those groups. The methoxy (OCH₃) group of PmAS has the highest chelation efficiency; thus, the PmAS pigment provided the best corrosion protection.

When incorporated into various paint formulations, all films containing polymer pigments were found to have good adhesion properties, good impact resistance, and high ductility and hardness compared to the control. Painted panels were immersed in sea water, and after 28 days, the PmAS panel showed little to no rusting compared to the other polymers tested. All of the polymers, however, exhibited some degree of blistering.

Bio-based aromatic acids have been studied for use as “green” corrosion inhibitors [54]. Salts of vanillic, cinnamic, ferulic, and mandelic acids were prepared by reacting each acid with an alkaline material. In immersion testing, the salts of vanillic, cinnamic, and ferulic acids provided excellent corrosion protection to a steel substrate due to their ability to adsorb onto the substrate and form a protective film that increased the electrical resistance [55]. While the results indicate that these pigments show potential for corrosion inhibition, and their environmentally friendly nature may be attractive to Reclamation, these pigments are currently more of a novelty. Much more research and testing must be completed before they can be considered a substitute for lead or chromate.

Metallic Pigments

Metallic zinc pigments are some of the most widely used protective pigments in coatings but generally offer corrosion protection to steel by acting as a sacrificial pigment and not as an inhibitive pigment [56].

Modern research has indicated that other metallic pigments may be successful corrosion inhibitors. Aluminum pigments, specifically aluminum flake pigments, have been studied on their own as corrosion inhibitors [57]. A patent filed in 2002 claims that a coating material comprised of high content (upwards of 25 percent by weight) of aluminum flakes can provide mechanical and UV protection to a metal substrate. The aluminum flakes have been found to lie flat on the surface, forming an interlocking scale-like structure that resists abrasion and is impermeable to corrosive agents. The matrix configuration protects the underlying surface and it is also protected from UV light.

In another application, aluminum pigments were coated with a layer of silica to enhance chemical stability and dispersibility [58]. Compared to bare aluminum pigments, the coated sol-gel pigments had better anticorrosive properties (determined by alkaline stability testing, which measured the time until 5 milliliters of hydrogen gas was formed, and boiling water testing, which measured the time it took for 410 milliliters of gas formation). For comparison, the uncoated aluminum failed both tests after less than 1 hour, while the coated aluminum lasted approximately 7 hours in the boiling water test and over 100 hours in the alkaline stability test. This improvement can be attributed to silica’s ability to react its negatively charged species with the substrate’s metallic cations to form a protective film, or passivation layer.

CONCLUSION

There has been a significant amount of research dedicated to finding a replacement for lead and chromate pigments in corrosion inhibiting coatings. While an attempt was made to survey a broad swath of the current research, there

is still an incredible amount that has not yet been reviewed. This work should be ongoing, especially as new pigments and technologies are continuously developed.

Further research is warranted for some of the pigments described in this review—especially the inorganic pigments that, like red lead, form metal soaps when reacted with certain binders. These pigments may also be the easiest to further analyze, as they can be found readily in bulk and would not need to be synthesized or formulated like some of the organic pigments. With that said, it is also worth doing further research on conducting polymers, specifically polyaniline. The use of polyaniline as a corrosion inhibiting pigment was discussed multiple times for a variety of different applications during review of the literature.

In addition, it is worthwhile to analyze commercially available coating systems that Reclamation currently does not use for the presence of some of the pigments discussed in this review. Analyzing currently available coating systems would be the quickest way to begin testing alternative inhibitive pigments. This type of work would not require Reclamation to have to formulate new coatings on its own. Reclamation could also engage with coatings manufacturers via cooperative agreements to aid in developing new formulations.

One of the biggest challenges in finding a suitable replacement for red lead and chromate pigments is shortening the testing cycle by finding ways to predict when or how a coating will fail [59]. This would save significant costs by allowing testing of more of the inhibitive pigments in a shorter timescale. In order for this to be achieved, a better understanding of the mechanisms of paint failure and how the individual components of a coating system interact to achieve the overall service lifetime is needed. Therefore, further research needs to be done to determine exactly how the coatings will fail and in what timeframe so that these signs can be identified early in the testing.

Replacing old legacy coatings systems such as lead-based paint with safe and modern equivalents is an important but challenging proposition for Reclamation. With further investigation into inhibitive pigments, including testing current offerings, formulating new components, and learning more about their failure mechanisms, service lives can be increased from the current 20–25 years to the desired 50+ years exhibited by legacy coatings.

RECOMMENDATIONS FOR FUTURE WORK

- Further investigation is warranted to identify additional pigments that offer similar corrosion protection as red lead and chromate pigments without the harmful health and environmental effects.

- Commercially available coating systems not currently used by Reclamation should be evaluated for the presence of certain pigments that have been identified to be corrosion inhibiting. Accelerated and field testing of these coatings should be performed to determine if they are more suitable for use than the current coatings used.
- Further research is needed to determine an expected service life and mechanism of failure for the modern pigments identified in this review as likely to be a nontoxic substitute for red lead and chromate.
- There is a need to account for the corrosion inhibition lag times exhibited by some pigments. Field testing, or exposing these specimens to a humid environment for a period of time before accelerated testing, may be necessary to ensure that pigments selected for further examination are analyzed appropriately and equally.
- Electrochemical impedance spectroscopy should also be employed to monitor the performance of coatings during field testing. The obtained data can then be extrapolated to project the service life.

REFERENCES

- [1] G. G. Wallace, P. R. Teasdale, G. M. Spinks, and L. A. P. Kane-Maguire, *Conductive Electroactive Polymers*, Boca Raton: CRC Press, 2008.
- [2] A. Kalendova, I. Sapurina, J. Stejskal, and D. Vesely, “Anticorrosion properties of polyaniline-coated pigments in organic coatings,” *Corrosion Science*, vol. 50, pp. 3549–3560, 2008.
- [3] M. A. A. El-Ghaffar, E. Youssef, W. Darwish, and F. Helaly, “A Novel Series of Corrosion Inhibitive Polymers for Steel Protection,” *Journal of Elastomers and Plastics*, vol. 30, pp. 68–94, 1998.
- [4] J. Nie, *Improvements in the Use of Mg Pigments in Corrosion Protective Coatings*, Fargo: UMI Dissertation Publishing, 2010.
- [5] NACE International, *Coating Inspector Program Level I*, Houston: NACE International, 2017.
- [6] American Water Works Association (AWWA), *External Corrosion—Introduction to Chemistry and Control*, Denver: American Water Works Association, 1987.
- [7] American Iron and Steel Institute, *Buried Steel Penstocks*, Washington D.C.: Construction Marketing Committee, American Iron and Steel Institute, 1998.
- [8] L. V. Charles Munger, *Corrosion Prevention by Protective Coatings*, Houston: NACE International, 2014.
- [9] G. Koch, J. Varney, O. M. M. G. Neil Thompson, and J. Payer, “International Measures of Prevention, Application, and Economics of Corrosion Technologies Study,” NACE International, Houston, 2016.
- [10] G. H. Koch, M. P. Brongers, N. G. Thompson, and J. P. Y. Paul Virmani, “Corrosion Costs and Preventative Strategies in the United States,” NACE International, Houston, 2002.
- [11] A. Popoola, O. Olorunniwo, and O. Ige, “Corrosion Resistance Through the Application of Anti-Corrosion Coatings,” in *Developments in Corrosion Protection*, InTech, 2014.

- [12] T. Gichuhi and D. Tarjan, *Corrosion Control Without the use of Toxic Heavy Metals*, Hammond: HALOX, 2016.
- [13] E. Ghali, *Corrosion Resistance of Aluminum and Magnesium Alloys: Understanding, Performance, and Testing*, Hoboken: John Wiley & Sons, 2010.
- [14] J. Sinko, "Challenges of chromate inhibitor pigments replacement in organic coatings," *Progress in Organic Coatings*, vol. 42, no. 3-4, pp. 267–282, 2001.
- [15] L. Fedrizzi, W. Furbeth, and F. Montemor, "Self-healing properties of new surface treatments," European Federation of Corrosion, Leeds, 2011.
- [16] A. H. Sabin, *Red-Lead and How to Use it in Paint*, New York City: John Wiley & Sons, Inc., 1917.
- [17] A. H. Sabin, "Protection of Metals Against Corrosion," in *The Industrial and Artistic Technology of Paint and Varnish*, New York City, John Wiley & Sons, Inc, 1927, pp. 240–331.
- [18] J. V. Koleske, *Paint and Coating Testing Manual*, Philadelphia: ASTM International, 1995.
- [19] M. Malik, M. Hashim, F. Nabi, S. AL-Thabaiti, and Z. Khan, "Anti-corrosion Ability of Surfactants: A Review," *International Journal of Electrochemical Science*, vol. 6, pp. 1927–1948, 2011.
- [20] J. Jobling and W. Petersen, "Soaps as Ferment-Inhibiting Agents," *The Journal of Experimental Medicine*, vol. 19, pp. 239–250, 1914.
- [21] Centeno, Catalano, Dybowski, Zumbulyadis, Yao, and Murphy, *Investigating the Formation and Structure of Lead Soaps in Traditional Oil Paintings*, New York City: The Metropolitan Museum of Art.
- [22] O. O. Knudsen and A. Forsgren, *Corrosion Control Through Organic Coatings*, Second Edition, Boca Raton: CRC Press, 2017.
- [23] G. Reinhard, M. Radtke, and U. Rammelt, "The role of the salts of weak acids in the chemical passivation of iron and steel in aqueous solutions," *Corrosion Science*, vol. 33, pp. 307–313, 1992.
- [24] G. Wright, *Corrosion Protection of Metals*, Auckland: University of Auckland, 1959.

- [25] J. Mayne and E. Ramshaw, "Inhibitors of the corrosion of iron. II. Efficiency of the sodium, calcium and lead salts of long chain fatty acids," *Journal of Chemical Technology and Biotechnology*, vol. 10, no. 10, pp. 419–422, 1960.
- [26] C. G. Dariva and A. F. Galio, "Corrosion Inhibitors — Principles, Mechanisms and Applications," in *Developments in Corrosion Protection*, InTech, 2014.
- [27] J. Davis, "Introduction," in *Corrosion of Aluminum and Aluminum Alloys*, Materials Park, ASM International, 1999, pp. 1–10.
- [28] SSPC, Good Painting Practice: SSPC Painting Manual Volume 1, Fourth Edition, Pittsburgh: SSPC: The Society for Protective Coatings, 2002.
- [29] A. Campbell, E. Williams and D. Barltrop, "Motor neurone disease and exposure to lead," *Journal of Neurology, Neurosurgery, and Psychiatry*, vol. 33, pp. 877–885, 1970.
- [30] M. Costa, "Toxicity and Carcinogenicity of Cr(VI) in Animal Models and Humans," *Critical Reviews in Toxicology*, vol. 27, no. 5, pp. 431–442, 1997.
- [31] H. L. Clever, M. E. Derrick, and S. A. Johnson, "The Solubility of Some Sparingly Soluble Salts of Zinc and Cadmium in Water and in Aqueous Electrolyte Solution," *Journal of Physical and Chemical Reference Data*, vol. 21, no. 5, pp. 941–1004, 1992.
- [32] J. Davis, Corrosion: Understanding the Basics, vol. 20, Materials Park: ASM International, 2000, pp. 47–51.
- [33] M. Pryor and M. Cohen, "The Inhibition of the Corrosion of Iron by Some Anodic Inhibitors," *Journal of The Electrochemical Society*, vol. 100, no. 5, pp. 203–215, 1952.
- [34] J. Mayne, "Paints for the Protection of Steel—a Review of Research into their Modes of Action," *British Corrosion Journal*, vol. 5, no. 3, pp. 106–111, 1970.
- [35] D. Weng, P. Jokiel, A. Uebleis, and H. Boehni, "Corrosion and protection characteristics of zinc and manganese phosphate coatings," *Surface and Coatings Technology*, vol. 88, pp. 147–156, 1996.

- [36] T. S. Narayanan, "Surface Pretreatment by Phosphate Conversion Coatings—a Review," *Reviews on Advanced Materials Science*, vol. 9, pp. 130–177, 2005.
- [37] M. Gimeno, M. Puig, S. Chamorro, and J. Molina, "Improvement of the anticorrosive properties of an alkyd coating with zinc phosphate pigments assessed by NSS and ACET," *Progress in Organic Coatings*, vol. 95, pp. 46–53, 2016.
- [38] N. Greenwood, *Chemistry of the Elements*, vol. 18, Oxford: Butterworth-Heinemann, 1997, pp. 268–270.
- [39] R. Lapasin, A. Papo, and G. Torriano, "New Shop Primers for Steel Based on Inhibitive Pigments of Low Toxicity," *British Corrosion Journal*, vol. 12, no. 2, pp. 92–102, 2013.
- [40] Springborn Laboratories, Inc., "Development of Non-Chromate Waterborne Wash Primer," Springborn Laboratories, Inc., Enfield, 1983.
- [41] American Conference of Governmental Industrial Hygienists, "TLVs: threshold limit values for chemical substances and physical agents and biological exposure indices," in *ACGIH*, Cincinnati, 1977.
- [42] D. Heijerick and S. Carey, "The toxicity of molybdate to freshwater and marine organisms: Generating additional chronic toxicity data for the refinement of safe environmental exposure concentrations in the US and Europe," *Science of the Total Environment*, vol. 609, pp. 420–428, 2017.
- [43] J. Mayne, "Corrosion Prevention by Paints," *Transactions of the IMF*, vol. 29, no. 1, pp. 146–163, 1952.
- [44] M. A. A. El-Ghaffar, N. M. Ahmed, and E. A. Youssef, "A method for preparation and application of micronized ferrite pigments in anticorrosive solvent-based paints," *Journal of Coatings Technology and Research*, vol. 7, no. 6, pp. 703–713, 2009.
- [45] I. Sekine and T. Kato, "Corrosion-Protective Properties of Various Ferrite Paint Films," *Industrial & Engineering Chemistry Product Research and Development*, vol. 25, no. 1, pp. 7–10, 1986.
- [46] S. H. Tan, *Organic Corrosion Inhibitors*, Western Australia: Murdoch University, 1991.

- [47] M. Kending, M. Hon, and L. Warren, ““Smart” corrosion inhibiting coatings,” *Progress in Organic Coatings*, vol. 47, no. 3, pp. 183–189, 2003.
- [48] P. Zarras, N. Anderson, C. Webber, D. Irvin, J. Irvin, A. Guenther, and J. Stenger-Smith, “Progress in using conductive polymers as corrosion-inhibiting coatings,” *Radiation Physics and Chemistry*, vol. 68, no. 3-4, pp. 387–394, 2003.
- [49] R. Patil and S. Radhakrishnan, “Conducting polymer based hybrid nano-composites for enhanced corrosion protective coatings,” *Progress in Organic Coatings*, vol. 57, no. 1, pp. 332–336, 2006.
- [50] B. Wessling, “Passivation of metals by coating with polyaniline: Corrosion potential shift and morphological changes,” *Advanced Materials*, vol. 6, no. 3, pp. 226–228, 1994.
- [51] ASTM International, *ASTM D714-87: “Evaluating Degree of Blistering of Paints,”* West Conshohocken: ASTM International, 2000.
- [52] ASTM International, *ASTM D1654-92: “Evaluation of Painted or Coated Specimens Subjected to Corrosive Environments,”* West Conshohocken: ASTM International, 2000.
- [53] ASTM International, *ASTM D610-85: “Evaluating Degree of Rusting on Painted Steel Surfaces,”* West Conshohocken: ASTM International, 2011.
- [54] M. Shen, A. Furman, and R. Kharshan, “Investigation of Bio-Based Aromatic Acids as Corrosion Inhibitors,” *Materials Performance*, vol. 55, no. 3, pp. 52–57, 2016.
- [55] E. Akbarzadeh, M. Ibrahim, and A. Rahim, “Monomers of lignin as corrosion inhibitors for mild steel: study of their behaviour by factorial experimental design,” *Corrosion Engineering, Science and Technology*, vol. 47, no. 4, pp. 302–311, 2012.
- [56] M. Gore and S. Smith, “Methods and Developments in Zinc-Based Anticorrosion Coatings,” *Materials Performance*, vol. 56, no. 1, pp. 34–37, 2017.
- [57] J. T. LeFave, “Method of protecting surfaces with aluminum flaked composition.” United States Patent US 6872767, 14 November 2002.

- [58] R. Supplit and U. Schubert, "Corrosion protection of aluminum pigments by sol-gel coatings," *Corrosion Science*, vol. 49, no. 8, pp. 3325–3332, 2007.
- [59] S. Lyon, R. Bingham, and D. Mills, "Advances in corrosion protection by organic coatings: What we know and what we would like to know," *Progress in Organic Coatings*, vol. 102, pp. 2–7, 2016.

ATTACHMENT A

Supporting Information

Datasets that Support the Final Report

The dataset used in the section “History of Inhibitive Pigment Use on Reclamation’s Structures” to illustrate use of red lead and chromate coatings in the Bureau of Reclamation’s (Reclamation) history can be found at the following share drive location:

T:\ENGRLAB\MERL\COATINGS_Project Data

The creators of this file were Allen Skaja (askaja@usbr.gov, 303-445-2396) and Stephanie Prochaska (sprochaska@usbr.gov, 303-445-2323).

This file contains information about historical coating data, including project name, structure(s) that was/were coated, the coating system used, whether or not it was an original coating, spot repair or recoat, and the date(s) that the coating was applied. The data were collected predominantly from reviewing old paper files, including, but not limited to, specifications, submittals, submittal responses, and memorandums.

This dataset is in no way inclusive of all historical coating projects completed by Reclamation.

Approximate file size: 120 kilobytes (KB)

